


AMENDMENTS TO THE CLAIMS:

This listing of claims will replace all prior versions, and listings, of claims in the application:

LISTING OF CLAIMS:

- B1
1. (Previously Presented) A modified acrylic polymer obtainable by reacting
- (A) a poly(acrylic acid) with endgroups resulting from initiators and/or chain transfer agents that are inert for condensation reactions, said poly(acrylic acid) A-1 having a molecular weight of from 500 to 20,000



and

- (B) o molar parts of a monofunctional polyalkyleneglycol-monoalkylether B-1




and/or, optionally

- (C) p molar parts of a monofunctional α -amino-polyalkyleneglycol- ω -alkylether C-1



and/or, optionally

- (D) q molar parts of a primary or secondary amine D-1



D-1

wherein R represents a hydrogen atom or a methyl group, or a mixture thereof;

M represents a hydrogen atom, a C₁ - C₅ alkyl rest or an alkali metal, an alkaline earth metal or other two or three valent metal atoms, an ammonium or organic ammonium group, or a mixture thereof;

each R¹ independently from each other is a C₁ - C₄ alkyl rest, A and B represent alkylene groups with 2 - 4 C-atoms, the mixture of (A-O) and (B-O) may be formed by either random addition or block addition, and (A-O) ≠ (B-O);

R² and R³ independently from each other represent a hydrogen atom, or an aliphatic, cycloaliphatic, araliphatic or aromatic rest, or R² and R³ may together with the nitrogen atom to which they are bound form a morpholine or imidazole ring system, or another ring systems containing at least one hetero atom like nitrogen, sulfur or oxygen; or R² and R³ independently from each other represent oxyalkylene groups of the structure R⁵-(O-R⁶)_v-, wherein R⁵ represents a C₁ - C₄ alkyl rest and O-R⁶ represents an oxyalkylene group with 2 to 4 carbon atoms, whereby within the same structure R⁵-(O-R⁶)_v-, O-R⁶ can represent more than one kind of oxyalkylene group, wherein the mixture may be formed by either random addition or block addition;

wherein a molar ratio of

31
 $a:o:p:q = 1:(0.1-0.95):(0-0.6):(0-0.6)$, [preferably $a:o:p:q = 1:(0.1-0.95):(0-0.3):(0-0.3)$, more preferably $a:o:p:q = 1:(0.1-0.95):(0-0.1):(0-0.1)$, still more preferably $a:o:p:q = 1:(0.1-0.95):(0-0.05):(0-0.05)$, even more preferably $a:o:p:q = 1:(0.1-0.95):(0-0.02):(0-0.02)$, and most preferably $a:o:p:q = 1:(0.1-0.95):(0-0.01):(0-0.01)$,] and

wherein $p + q < 0.9$, and

$o + p + q \leq a$;

r, s, t, u and v independently represent integers from 0 - 250;

$r + s > 1$;

$t + u > 1$;

in the presence of a catalyst at elevated temperatures following a certain kinetic influenced by the ratio of A-1, B-1 and/or, optionally C-1 and/or D-1 and temperature, in which the reaction can be followed by the decrease of the acid number over time, in which the reaction can be stopped at different reaction times resulting into polymers with different properties, said reaction is stopped

I. at a high slope of decrease of the acid number over the time resulting in polymers with a high initial water reduction and a decreasing slump flow over time


or

II. at a medium slope of decrease of the acid number over time resulting in polymers with a high or medium initial water reduction and a constant slump flow over the time


or

III. at a small slope of decrease or no decrease of the acid number over time resulting in polymers with a medium or low initial water reduction and an increasing slump flow over the time.


2. (Previously Presented) A modified acrylic polymer, obtainable by the reaction defined in claim 1 which is composed of m molar units of the group given by formula A below, o molar units of the group given by formula B below, optionally p molar units of the group given by formula C below, and/or optionally q molar units of the group given by formula D below, whereby:




A



B



C



D

wherein R represents a hydrogen atom or a methyl group, or mixture thereof;

M represents a hydrogen atom, a C₁ - C₅ - alkyl rest or an alkali metal, an alkaline earth metal or other two or three valent metal atoms, an ammonium or organic ammonium group, or a mixture thereof;

each R¹ independently from each other is a C₁ - C₄ alkyl rest, A and B represent alkylene groups with 2 - 4 C-atoms, the mixture of (A-O) and (B-O) may be formed by either random addition or block addition, and (A-O) ≠ (B-O);

R² and R³ independently from each other represent a hydrogen atom, or an aliphatic, cycloaliphatic, araliphatic or aromatic rest, or R² and R³ may together with the nitrogen atom to which they are bound form a morpholine or imidazole ring system, or another ring systems containing at least one hetero atom like nitrogen, sulfur or oxygen; or R² and R³ independently from each other represent oxyalkylene groups of the structure R⁵-(O-R⁶)_v-, wherein R⁵ represents a C₁ - C₄ alkyl rest and O-R⁶ represents an oxyalkylene group with 2 to 4 carbon atoms, whereby within the same structure R⁵-(O-R⁶)_v-, O-R⁶ can represent more than one kind of oxyalkylene group, wherein the mixture may be formed by either random addition or block addition;

r, s, t, u and v independently represent integers from 0 - 250;

$r + s > 1$;

$t + u > 1$;

B1
m, o, p, q are numerical values representing the molarity of the constituent units A, B, C and D present in the polymers, in a proportion of

$m:o:p:q = (0.05 - 0.9):(0.1-0.95):(0-0.6):(0-0.6),$

and wherein $p + q < 0.85$,

and $m + o + p + q = 1$.

3. (Previously Presented) The modified acrylic polymer according to claim 1, characterized in that the number average molecular weight is from 4000 to 100,000.

4. (Previously Presented) The modified acrylic polymer according to claim 1, wherein it is obtainable by a synthesis wherein the reactant A-1 has a number average molecular weight of from 1000 to 10,000.

5. (Previously Presented) The modified acrylic polymer according to claim 1, wherein it is obtainable by a synthesis wherein the reactant B-1 has a number average molecular weight of from 250 to 10,000 and the reactant C-1 has a number average molecular weight of from 250 to 10,000.

B1
6. (Previously Presented) The modified acrylic polymer according to claim 1, wherein it is obtainable by reacting reactants A-1 and B-1, and optionally C-1 and/or D-1 in the presence of an acid catalyst at a temperature of about 140°C to 250°C.

7. (Previously Presented) The modified acrylic polymer according to claim 1, wherein it is obtainable by a synthesis that is carried out using inert organic solvents as carrier.

8. (Previously Presented) The modified acrylic polymer according to claim 1, obtainable by using reactants A-1 and B-1, and optionally C-1 and/or D-1, whereby the reaction was stopped at a high slope of the decrease of the acid number over the time resulting in a polymer with a high initial water reduction and a decreasing slump flow over time, which can be used especially for precast applications.

9. (Previously Presented) The modified acrylic polymer according claim 1, obtainable by using reactants A-1 and B-1, and optionally C-1 and/or D-1, whereby the reaction was stopped at a medium slope of the decrease of the acid number over the time resulting in a polymer with a high or medium initial water reduction and a constant slump flow over time, which can be used especially for readymix applications.

10. (Previously Presented) The modified acrylic polymer according to claim 1, obtainable by using reactants A-1 and B-1, and optionally C-1 and/or D-1, whereby the reaction was stopped at a small slope of the decrease of the acid number over the time to linear behavior

resulting in a polymer with a medium or low initial water reduction and an increasing slump flow over time, which can be used especially for slump flow increasing applications.

11. (Previously Presented) The modified acrylic polymer according to claim 1, wherein $p + q \neq 0$.

12. (Previously Presented) An admixture in liquid or solid form comprising at least one modified acrylic polymer according to claim 1.

13. (Previously Presented) The admixture of claim 12, which comprises at least two modified acrylic polymers in various ratios resulting in an admixture with high water reduction and constant slump flow over time.

14. (Previously Presented) The admixture of claim 12 further comprising dispersing agents selected from the group consisting of sulfonated melamine condensates, sulfonated naphthalene condensates, lignosulfonates, substituted maleamid-vinyl-copolymers and acrylic or methacrylic copolymers with polyalkyleneglycol side chains, and mixtures thereof.

15. (Previously Presented) A mortar, concrete, cement or cementitious binder, containing at least one modified acrylic polymer according to claim 1 in an amount of 0.01 to 10% by weight of the binder, said mortar or concrete having a unit content of binder composition of 100

to 800 kg/m³, whereby said binder composition is selected from the group consisting of a cement, a mixture of cement, a latent hydraulic powder, a mixture of latent hydraulic powders, and mixtures thereof optionally together with one or more inert microscopic powder(s).

B1
16. (Previously Presented) The mortar, concrete, cement or cementitious binder according to claim 15, wherein the cement is selected from the group consisting of Portland cement, white cement, high alumina cement, blended cement, and mixtures thereof, and the latent hydraulic or inert microscopic powder is selected from the group consisting of fly ash, slag, natural pozzolane, silica fume, burnt oil shale, metakaolin calcium carbonate, and mixtures thereof.

17. (Previously Presented) The mortar, concrete, cement or cementitious binder according to claim 15, wherein the admixture in liquid or powder form containing the modified acrylic polymers is added before, during or after the grinding operation of the cement or the cementitious binder.

18. (Previously Presented) An aqueous slurry of microscopic powder containing a modified acrylic polymer according to claim 1, or a mixture thereof, in an amount of 0.01 to 10% by weight of the binder.

19. (Previously Presented) The aqueous slurry of microscopic powder according to claim 18, wherein the microscopic powder is calcium carbonate, gypsum or gypsum based.

19 20. (Previously Presented) The modified acrylic polymer according to claim 1, whereby at least 0.5 mole-% of **B-1** is represented by a structure in which A represents an alkylene group with 2 C-atoms and $s=0$, or in which B represents an alkylene group with 2 C-atoms and $r=0$.

21. (Previously Presented) The modified acrylic polymer according to claim 1, whereby 5 - 100 mole-% of **B-1** is represented by a structure in which A represents an alkylene group with 2 C-atoms and $s=0$, or in which B represents an alkylene group with 2 C-atoms and $r=0$.

22. (Previously Presented) The modified acrylic polymer according to claim 1, whereby at least 0.5 mole-% **C-1** is represented by a structure in which A represents an alkylene group with 2 C-atoms and $u=0$, or in which B represents an alkylene group with 2 C-atoms and $t=0$.

23. (Previously Presented) The modified acrylic polymer according to claim 1, whereby 5 - 100 mole-% **C-1** is represented by a structure in which A represents an alkylene group with 2 C-atoms and $u=0$, or in which B represents an alkylene group with 2 C-atoms and $t=0$.

24. (Previously Presented) The modified acrylic polymer according to claim 1, wherein the molar ratio $a:o:p:q = 1:(0.1-0.95):(0-0.3):(0-0.3)$.

25. (Previously Presented) The modified acrylic polymer according to claim 1, wherein the molar ratio $a:o:p:q = 1:(0.1-0.95):(0-0.1):(0-0.1)$.

26. (Previously Presented) The modified acrylic polymer according to claim 1, wherein $p + q < 0.6$.

27. (Previously Presented) The modified acrylic polymer according to claim 1, wherein $p + q < 0.3$.

28. (Previously Presented) The modified acrylic polymer according to claim 2, whereby at least 0.5 mole-% of **B** is represented by a structure in which A represents an alkylene group with 2 C-atoms and $s=0$, or in which B represents an alkylene group with 2 C-atoms and $r=0$.

29. (Previously Presented) The modified acrylic polymer according to claim 2, whereby 5-100 mole-% of **B** is represented by a structure in which A represents an alkylene group with 2 C-atoms and $s=0$, or in which B represents an alkylene group with 2 C-atoms and $r=0$.

30. (Previously Presented) The modified acrylic polymer according to claim 2, whereby 0.5 mole-% of the formula **C** is represented by a structure in which A represents an alkylene group with 2 C-atoms and $u=0$, or in which B represents an alkylene group with 2 C-atoms and $t=0$.

31. (Previously Presented) The modified acrylic polymer according to claim 2, whereby 5-100 mole-% of the formula C is represented by a structure in which A represents an alkylene group with 2 C-atoms and $u=0$, or in which B represents an alkylene group with 2 C-atoms and $t=0$.

32. (Previously Presented) The modified acrylic polymer according to Claim 2, wherein $m:o:p:q = (0.05-0.9):(0.1-0.95):(0-0.3):(0-0.3)$.

33. (Previously Presented) The modified acrylic polymer according to claim 2, wherein $m:o:p:q = (0.05-0.9):(0.1-0.95):(0-0.1):(0-0.1)$.

34. (Previously Presented) The modified acrylic polymer according to claim 2, wherein $p + q < 0.6$.

35. (Previously Presented) The modified acrylic polymer according to claim 2, wherein $p + q < 0.3$.

36. (Previously Presented) The modified acrylic polymer according to claim 11, wherein $0 < p + q < 0.85$.

37. (Previously Presented) The modified acrylic polymer according to claim 11, wherein $0 < p + q < 0.6$.

38. (Previously Presented) An admixture in liquid or solid form comprising at least one modified acrylic polymer according to claim 8.

Please add the following claims:

39. (New) The modified acrylic polymer according to claim 1, wherein $p+q < 0.1$.

40. (New) The modified acrylic polymer according to claim 1, wherein $p+q < 0.02$.

41. (New) The modified acrylic polymer according to claim 1, wherein $p+q < 0.01$.

42. (New) The modified acrylic polymer according to claim 2, wherein $p+q < 0.1$.

43. (New) The modified acrylic polymer according to claim 2, wherein $p+q < 0.02$.

44. (New) The modified acrylic polymer according to claim 2, wherein $p+q < 0.01$.

45. (New) The modified polymer according to claim 1, wherein the molar ratio $a:o:p:q = 1:(0.1-0.95):(0-0.02):(0-0.02)$.

46. (New) The modified acrylic polymer according to claim 1, wherein the molar ratio $a:o:p:q = 1:(0.1-0.95):(0-0.01):(0-0.01)$.

47. (New) The modified acrylic polymer according to claim 2, wherein the molar ratio $a:o:p:q = 1:(0.1-0.95):(0-0.02):(0-0.02)$.

β2 48. (New) The modified acrylic polymer according to claim 2, wherein the molar ratio $a:o:p:q = 1:(0.1-0.95):(0-0.01):(0-0.01)$.

